



### **▶** RoHS

### Products / Interface Materials / Adhesives

# Thermal Adhesives

Ther-O-Bond 1500

Epoxy casting system for potting and encapsulation

Ther-O-Bond 1600

Two part epoxy for bonding

Ther-O-Bond 2000

Rapid cure acrylic adhesive

#### Thermalbond™

High strength epoxy adhesive

Adhesives offer excellent heat transfer and high voltage isolation. Epoxy adhesives offer low shrinkage, and coefficients of thermal expansion comparable to copper or aluminum. They bond readily to metals, glass, ceramics, and most plastics.

### Ther-O-Bond 1500

Ther-O-Bond 1500 is a versatile epoxy casting system developed for high performance, production potting and encapsulating applications where low shrinkage and rapid air evacuation are required. This formulation has a very low surface tension and a flowable viscosity, which affords excellent air release. Ther-O-Bond 1500 adhers to rigid plastics and laminates, metals and ceramics, has a low coefficient of thermal expansion and is readily machined and shaped with ordinary shop tools. The fully cured epoxy system is an excellent electrical insulator which provides good resistance to electrolysis, leakage and corrosion room water, weather, gases and chemical compounds.

# **Ordering Information**

<u> </u>						
Description	Part Number	RoHS	PCN	Package/ Kit	Size	
Ther-O- Bond 1500	159900F00000G	RoHS √ Compliant	Product Change Notice	Resin and Hardener	.946 liter (1 Qt.)	

### **Handling Characteristics**

Mix Ratio by Weight, Resin to Hardener:	100 to 15	
Mixed Viscosity @ 25°C, cps:	1000 - 1500	
Work-Life @ 25°C	45 Minutes	
Gel Time @ 25°C	3-6 Hours	
Cure Schedule @ 25°C	8 Hours	
Cure Schedule @ 65°C	1 Hour	
Cure Schedule @ 100°C	0.5 Hour	

### **Physical Properties**

Filysical Flope		
Color	Black	
Specific Gravity	1.50	
Operating Temp, °C	-60 to 155	
Heat Distortion Temp, °C	100	
Hardness, Shore D:	88	
Thermal Conductivity W/ (m°C)	1.26	
Compressive Strength, psi	14,000	
Dissipation Factor, 100 KIIz @25°C	0.01	
Self Extinguishing?:	yes	
C.T.E. (ppm/°C)	25	
Tensile Strength (@25° C)	9200 psi	
Dielectric Strength (volts/ mil)	800	
Shelf Life (DOM)	18 months <sup>1</sup>	

(1) Stated shelf life is from date of manufacture. To allow for inventory cycle, product shipped from Aavid will have less than 18 months remaining shelf life. Aavid guarantees a minimum of 3 months remaining shelf life. Please adjust order quantity so all product will be consumed with in 3 months of date of shipment.

# Ther-O-Bond 1500 Resistance Calculator

Enter the area of the device that will contact the heat sink:	mm²
Enter the grease thickness:	mm
Interface Resistance =	

### Formula

interface resistance= interface thickness (mm) \* 1000

thermal conductivity (W/m-K) \* contact area (mm²)

Product Name: THER-O-BOND 1500 RESIN

MSDS No.: 11-000356

Page: 1 of 4

# RESIN TECHNOLOGY GROUP, LLC

MATERIAL SAFETY DATA SHEET

# 1. MATERIAL IDENTIFICATION

Froduct Name:

THER-O-BOND 1500 RESIN

2. COMPOSITION			Exposu	Exposure Limits	
HAZARDOUS COMPONENTS	CAS N	O. PERCENT	ACGIH TLV-TWA	OSHA PEL	
Epoxy Resin N - Butyl Glycidyl Ether	25068-3 2426-08		N.E. 133 mg/m³	N.E. 133 mg/m³	

Note: Due to this product's physical composition, the release or generation of dust is not expected to occur under normal conditions of use. Abbreviations: N.E.: Not Established

### 3. HEALTH HAZARDS IDENTIFICATION

Primary Routes of Exposure:

Eyes: Yes

Skin: Yes

Inhalation: Yes

Eye Contact:

Contact can cause moderate irritation.

Skin Contact:

Contact can cause moderate irritation; contact with this product at elevated temperatures can result in thermal burns.

Inhalation:

May cause irritation to the respiratory tract.

Ingestion:

May be slightly toxic and may be harmful if swallowed.

### 4. FIRST AID MEASURES

Eyes:

Flush eyes thoroughly with water for 15 minutes while holding eyelids open. Seek medical attention immediately,

Skip:

Remove contaminated clothing and shoes. Wipe excess from skin. Flush skin with water. Follow by washing with

soap and water. If irritation occurs, seek medical attention. Do not reuse clothing until laundered.

Inhalation:

Remove to fresh air, and provide oxygen if breathing is difficult. Consult a physician.

Ingestion:

If large quantities are ingested, give no more than 2 glasses of water and induce vomiting by giving 30 cc (2 tablespoons) syrup of Ipecae, or by sticking finger to back of victim's throat. Seek medical attention promptly.

Product Name: THER-O-BOND 1500 RESIN

MSDS No.: 11-000356

Page: 2 of 4

### 5. FIRE FIGHTING MEASURES

### FLAMMABLE PROPERTIES

Flashpoint: 270 °F (PMCC)
Explosive Limits: Not available.
Auto-Ignition 'Temperature: Not available.

Hazardous Decomposition Products:

Carbon monoxide, aldehydes, acids and other organic substances may be formed during

combustion or elevated (>500 °F) temperature degradation.

Fire Fighting Instructions:

Firefighters should wear full bunker gear including a positive pressure NIOSII approve self-contained

breathing apparatus. Cool fire exposed containers with water.

Exlinguishing Media:

Use water fog, foam, dry chemical, or carbon dioxide.

# 6. ACCIDENTAL RELEASE MEASURES

Wear respirator and protective clothing as appropriate. Ventilate area if necessary, evacuate if airborne levels could exceed established limits. Soak up residue with an absorbent such as clay, sand or other suitable material. Dispose of properly. Flush area with water to remove trace residue.

### 7. HANDLING AND STORAGE

Store in a cool dry place away from open flames and high temperatures. Heating this resin above 300 °F in the presence of air may cause slow oxidative decomposition above 500 °F, polymerization may occur. Some curing agents, e.g. aliphatic polyamines, can produce exothermic reactions, which in large masses can cause runaway polymerization. Funes and vapors from these thermal and chemical decompositions vary widely in composition and toxicity. Do not breathe finnes.

### 8. EXPOSURE CONTROLS AND PERSONAL PROTECTION

Engineering/Ventilation Controls: General ventilation and or local exhaust may be required to maintain airborne concentrations

below established exposure limits when generating vapors or mists.

Respiratory Protection: Where exposure exceeds established airborne limits, use a NIOSH approved respirator, or a

self-contained breathing apparatus, or a supplied air respirator as necessary to control exposure.

Skin Protection: Wear impervious gloves and protective clothing as necessary to prevent skin contact.

Eye Protection: Wear chemical splash goggles or safety glasses with side shields.

# 9. PHYSICAL AND CHEMICAL PROPERTIES

Appearance: Black liquid

Odor: Sweet, pleasant odor Boiling Point: Not established.

 Specific Gravity:
 1.55

 Vapor Pressure:
 1

 Vapor Density (air=1):
 3.8

Evaporation Rate: Not applicable Solubility in Water: Negligible