1. Base Data

| Part No.                               | 319-00600  |
|--|--|
| Туре                                   | TREDUX-6/2   |
| Color                                  | Black (BK)   |
| Features                               | TREDUX is a thin wall, flexible tubing with a shrink ratio of 3:1 and is made from cross-linked polyolefin. Available in 1 m lengths, 9 sizes from 1.5 mm to 101.6 mm and colours black and yellow/green. All 1 m lengths are delivered in a display carton. |
| Application                            | TREDUX thin wall heatshrink tubing is used for general electrical insulation and mechanical protection of cables and wires.  |
| shortdescription50character            | Thin wall heat shrink tubing; 3:1 ratio  |
| Shrink Ratio                           | 3:1  |
| Size                                   | 6/2  |
| Variant                                | Thin-Wall  |
| Voltage range                          | 600 V  |
| 2. Product Dimensions                  |  |
| Length (L)                             | 39.36 " / 1.0 m  |
| Wall Thickness (WT)                    | .027   |
| Wall Thickness                         | 0.70 mm  |
| Longitudinal change after<br>shrinkage | +/-5% max.   |
| Recov. Ø d max.                        | 2.0 mm   |
| Recovered Ø                            | .08 "  |

## **Supplied Ø** .236 " / 6.0 mm

## 4. Material and Specifications

| Material                | Polyolefin, cross-linked (POX)   |
|-------------------------|--|
| Material Shortcut       | POX  |
| Certification           | SAE - AMS - DTL-23053/5 Class 2 (clear) / SAE-AMS-DTL-23053/5 Class 1<br>and 3 |
| Certification           | UL224 125 °C 600V VW-1   |
| Copper corrosion        | tested according to UL 224   |
| Dielectric Strength     | 20 kV/mm according to ASTM D 150   |
| Elongation at break     | 500%(ASTM D 2671)  |
| Flammability            | UL224 VW-1 (except clear)  |
| Insulation Class        | B (VDE 0530)   |
| Min. Shrink Temperature | +100 °C  |
| Operating Temperature   | -67 °F to +275 °F (-55 °C to +135 °C)  |
| ROHS Conformity         | Rohs   |