

RTV Silicones by  **MOMENTIVE**  
performance materials  
**1-Part Adhesive Sealant RTV157**



▶ SPECIAL ORDER

**Primary Characteristics**

- ▶ Gray Paste
- ▶ Excellent weatherability
- ▶ Resists ozone and chemicals
- ▶ High Strength
- ▶ Acetoxy cure

Use for high strength adhesive gasketing, maintenance and electrical insulation. Highly flexible consistency when cured.

Available Sizes

Catalog Number	Sizes Available	Description
RTV157-85ML	85 mL (2.8 oz)	Tube

Specifications

Use	Adhesive Sealant
Special Feature	High Strength
Cross Reference	RTV157
<b>Uncured Properties</b>	
Consistency	Paste
Color	Gray
Specific Gravity	1.09
Tack Free Time	45 minutes
Cure through time	7 days
Useful Temp. Range	-60°C to 204°C (-75°F to 400°F)
<b>Cured Properties - MECHANICAL</b>	
<a href="#">Hardness</a>	28 (Shore A)
Tensile Strength	6.21 MPa (975 psi)
Elongation	825%
<b>Cured Properties - ELECTRICAL</b>	
Dielectric Strength	20.7 kV/mm (525 V/mil)
Dielectric Constant	2.9 @ 60 Hz
<b>Other</b>	
<a href="#">Viscosity</a> (@ 25°C)	155 g/min