

RTV Silicones by  **MOMENTIVE**
performance materials
2-Part Adhesive Sealant RTV230



Primary Characteristics

- ▶ Fast cure time at room temperature
- ▶ No heat required to cure
- ▶ Fast property build
- ▶ Fast cure through time (approx. 30 minutes)
- ▶ Patented cartridge mixes as it is dispensed
- ▶ Excellent primerless adhesion to many substrates
- ▶ UL94 / FDA compliance pending
- ▶ Designed to offer high levels of productivity
- ▶ No cure inhibition concerns

A thixotropic, two component, room temperature curing silicone adhesive offering faster cure (a tack free time of approximately six minutes), a cure through time of 30 minutes, and primerless adhesion to a wide variety of substrates.

Available Sizes

Catalog Number	Sizes Available	Description	
RTV230-274ML	274ML (9.2 fl. oz)	2 part cartridge	▶ SPECIAL ORDER
RTV-230A-5G	5 gallon	Part A pail	▶ SPECIAL ORDER
RTV-230A-55G	55 gallon	Part A drum	▶ SPECIAL ORDER
RTV-230B-5G	5 gallon	Part B pail	▶ SPECIAL ORDER

Specifications

Use	Adhesive Sealant
Special Feature	Fast cure at room temperature
Standards	FDA compliance pending
	UL 94 HB pending
Cross Reference	SnapSil RTV 230A/B
Cured Physical Properties	
Color	White
Specific Gravity (@ 23°C)	1.40
Viscosity	RTV230A: 710,000 cps RTV230B: 95,000 cps
Application rate @ 45 psi	RTV230A: 250 g/min RTV230B: 280 g/min
Tensile Strength	255 psi
Elongation	280%
Hardness	36 (Shore A)
Work (pot) life	5 to 15 minutes